

96-0086

The invention relates to the building materials and may be used at the plastering compositions production.

The plastering composition includes, mass%: β - semihydrate of calcium sulphate 35-40; calcium quicklime 4,0-4,6; gellike hydroxy ethylcellulose 2,6-2,7; tartaric acid 0,04-0,06; surfactants 0,02-0,025; fine grounded limeston - the rest.

Composition life time 140-160 min. viability 40-65 min., compressive strength 4,2-4,8 Mpa.

The technical result of the invention consists in the reducing of the production labour input of the working plaster compositions and in increasing viability thereof.